


AFD: 22.3 μ
SD: 5.0 μ
CV: 22.4 %
CF: 92.6 %
Curve: 12.8 Dg/mm
Min: 22.1 μ
Max: 25.0 μ
Staple: 95.0 mm


% of Fibers



Alpaca Fiber Testing USA

Fiber Diameter (microns)

AFD: 22.3 μ
SD: 5.0 μ
CV: 22.4 %
CF: 92.6 %
Curve: 12.8 Dg/mm
Min: 22.1 μ
Max: 25.0 μ
Staple: 95.0 mm



Alpaca Fiber Testing USA