


AFD: 23.0 μ
SD: 4.7 μ
CV: 20.5 %
CF: 92.8 %
Curve: 13.6 Dg/mm
Min: 22.0 μ
Max: 24.5 μ
Staple: 100.0 mm

% of Fibers



Alpaca Fiber Testing USA

Fiber Diameter (microns)

AFD: 23.0 μ
SD: 4.7 μ
CV: 20.5 %
CF: 92.8 %
Curve: 13.6 Dg/mm
Min: 22.0 μ
Max: 24.5 μ
Staple: 100.0 mm

