


LANTANA

AFD: 21.9 μ
SD: 4.6 μ
CV: 20.9 %
CF: 95.1 %
Curve: 14.8 Dg/mm
Min: 20.3 μ
Max: 24.5 μ
Staple: 0.0 mm

% of Fibers



Alpaca Fiber Testing USA

LANTANA

AFD: 21.9 μ
SD: 4.6 μ
CV: 20.9 %
CF: 95.1 %
Curve: 14.8 Dg/mm
Min: 20.3 μ
Max: 24.5 μ
Staple: 0.0 mm

