


**AFD:** 22.3  $\mu$   
**SD:** 4.6  $\mu$   
**CV:** 20.4 %  
**CF:** 94.8 %  
**Curve:** 12.2 Dg/mm  
**Min:** 21.8  $\mu$   
**Max:** 23.7  $\mu$   
**Staple:** 120.0 mm

% of Fibers



*Alpaca Fiber Testing USA*

Fiber Diameter (microns)

# SHILOH

**AFD:** 22.3  $\mu$   
**SD:** 4.6  $\mu$   
**CV:** 20.4 %  
**CF:** 94.8 %  
**Curve:** 12.2 Dg/mm  
**Min:** 21.8  $\mu$   
**Max:** 23.7  $\mu$   
**Staple:** 120.0 mm

