


TWISTER

AFD: 33.3 μ
SD: 8.5 μ
CV: 25.6 %
CF: 44.1 %
Curve: 9.1 Dg/mm
Min: 31.6 μ
Max: 36.6 μ
Staple: 90.0 mm

% of Fibers

Alpaca Fiber Testing USA



Fiber Diameter (microns)

TWISTER

AFD: 33.3 μ
SD: 8.5 μ
CV: 25.6 %
CF: 44.1 %
Curve: 9.1 Dg/mm
Min: 31.6 μ
Max: 36.6 μ
Staple: 90.0 mm

